

TEB

Triethylborane

TEB is a co-catalyst product soluble in aromatic and saturated aliphatic and cycloaliphatic hydrocarbons. Used in a chromium catalyst system.

CAS number
97-94-9

EINECS/ELINCS No.
202-620-9

TSCA status
listed on inventory

Composition

Triethylborane	^a ≥ 95.0 molar%
----------------	----------------------------

Characteristics

Appearance	Clear, colorless liquid
Boiling point, 760 mm Hg	95 °C
Density, 30 °C	0.675 g/cm ³
Melting point	-93 °C
Solubility	Soluble in aromatic and saturated aliphatic and cycloaliphatic hydrocarbons
Stability to air	Ignites upon exposure
Stability to water	Unreactive (and immiscible) with water
Viscosity, 25 °C	0.3 mPa.s

Thermochemical properties

Heat of vaporization ΔH_v , NBP	^b 377 J/g (90 cal/g)
Specific heat, 57 °C	2.276 J/g.°C (0.544 cal/g.°C)
Heat of formation ΔH_f° , 25 °C / 1 bar	-188 kJ/mole (-45 kcal/mole)
Heat of combustion ΔH_c° , 25 °C	-4975 kJ/mole (-1189 kcal/mole)

Notes:

^a Analyzed by a combination of gas chromatography, laser Raman spectroscopy, and ¹H or ¹¹B nuclear magnetic resonance spectroscopy. ^b NBP = Normal Boiling Point i.e. temperature at which the vapor pressure is 760 mm Hg (1 bar).

Applications

TEB may be used in organic synthesis as an agent for stereochemical control. TEB is also used as an adjuvant for Ziegler-Natta and silica-supported chromium catalysts for olefin polymerization.

Storage

TEB and its solutions are stable when stored under a dry, inert atmosphere and away from heat. TEB decomposes slowly at elevated temperatures. Thermal decomposition products include ethylene and alkylboranes.

Packaging and transport

TEB and its solutions are available worldwide in cylinders and portable tanks. In North America only, TEB is also available in tank trailers and rail cars. Containers are fabricated from carbon steel and are equipped with dip tubes for top discharge and all connections are located in the vapor space. Both packaging and transport meet the international regulations.

Safety and handling

TEB ignites upon exposure to air (burns with a green flame). Hydrocarbon solutions of TEB may also ignite upon exposure to air. TEB reacts with carboxylic acids and alcohols, but is virtually unreactive with water. However, it is prudent to keep water out of TEB process equipment in the event that other metal alkyls might be used in such equipment. TEB and its solutions must be handled under an inert atmosphere, e. g. , nitrogen or argon. Products of complete combustion of TEB and its solutions are boron oxides, carbon dioxide and water. TEB causes severe burns to the skin and eyes. It is imperative that proper personal protective equipment be worn when handling TEB. Wearing a self-contained breathing apparatus is also recommended while handling TEB. Please refer to the Material Safety Data Sheet (MSDS) for further information on the safe storage, use and handling of TEB. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available at <https://polymerchemistry.nouryon.com>. Additional information is provided in a technical bulletin entitled Properties of Alkylboranes from Nouryon. Copies may be obtained through your Nouryon representative.

Additional information

Availability: TEB is a commercial product available as the neat pyrophoric liquid and as pyrophoric and non-pyrophoric solutions in a variety of solvents. Consult your Nouryon representative for further information.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Contact Us

Europe, Middle East, India and Africa
polymerchemistry.nl@nouryon.com

Asia Pacific
polymerchemistry.ap@nouryon.com

Americas
polymerchemistry.na@nouryon.com

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font. The 'N' is significantly larger and more prominent than the rest of the text.